

ALVARO

TECHNICAL CHARACTERISTICS / TEKNİK ÖZELLİKLER

| COMPOSITION/İÇERİK | BACKING/ZEMİN |
|---|----------------|
| VINYL / URETHANE TOP COAT VİNİL / POLİÜRETAN YÜZEY | %100 POLYESTER |

| TEST TYPES / TEST TİPİ | ASPECT / KRİTER | NORM | UNIT / BİRİM | STANDART TEST |
|--|--------------------------------|-----------|--------------------|---------------|
| WEIGHT / AĞIRLIK | | 520 ± 40 | g / m ² | ISO 2286-2 |
| MARTINDALE - ABRASION / AŞINMA DAYANIMI | | > 22.000 | RUB | ISO 5470-2 |
| TEAR STRENGTH / YIRTILMA DİRENCİ | ACROSS / EN | > 40 | N | ISO 4674-1 |
| | ALONG / BOY | > 40 | N | ISO 4674-1 |
| TENSILE STRENGTH / KOPMA DİRENCİ | ACROSS / EN | > 150 | N | ISO 1421 |
| | ALONG / BOY | > 150 | N | ISO 1421 |
| ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA | ACROSS / EN | 100 ± 20% | % | ISO 1421 |
| | ALONG / BOY | 65 ± 20% | % | ISO 1421 |
| COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI | DRY / KURU | ≥ 4 | GS | ISO 105-X12 |
| | WET / ISLAK | ≥ 4 | GS | ISO 105-X12 |
| LIGHT FASTNESS / IŞIK HASLIĞI | LIGHT COLORS / AÇIK RENKLER | ≥ 4 | BW | ISO 105-B02 |
| | DARK COLORS / KOYU RENKLER | ≥ 5 | BW | ISO 105-B02 |



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

/floksertekstil

