

GALATA FR

TECHNICAL CHARACTERISTICS / TEKNİK ÖZELLİKLER

SURFACE/YÜZEY	BACKING/ZEMİN
VINYL / URETHANE TOP COAT VİNİL/POLİÜRETAN YÜZEY	%100 POLYESTER

TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		600 ± 5%	g/m ²	ISO 2286-2
TENSILE STRENGTH / KOPMA DİRENCİ	ACROSS / EN	> 400	N	ISO 1421
	ALONG / BOY	> 250	N	ISO 1421
TEAR STRENGTH / YIRTILMA DİRENCİ	ACROSS / EN	> 40	N	ISO 4674-1
	ALONG / BOY	> 30	N	ISO 4674-1
ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA	ACROSS / EN	250 ± %20	%	ISO 1421
	ALONG / BOY	75 ± %20	%	ISO 1421
ADHESION / YAPIŞMA		> 40	N	ISO 2411
MARTINDALE - ABRASION / AŞINMA DAYANIMI		> 50000	RUB (12kPa)	ISO 5470 - 2
MARTINDALE - ABRASION / AŞINMA DAYANIMI		> 50.000	RUB	EN ISO 12947: 1999 Part 2
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	≥ 4 - 5	GS	ISO 105X12
	WET / ISLAK	≥ 4 - 5	GS	ISO 105X12
LIGHT FASTNESS / IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	≥ 3	BW	ISO 105B02
	DARK COLORS / KOYU RENKLER	≥ 4	BW	ISO 105B02
WATERPROOF / SU GEÇİRMEZLİK	Hydrostatic Head	OK	60 cm/ perminute	BS3424 Part 26
FLAME RETARDANCY / GÜÇ TUTUŞURLUK	BS 5852 Part 1 Ignition Source 0,1 (Cigarette & Match) EN 1021 part 1 and 2 BS 7176 Low Hazard FMVSS 302 (FR Standart of Motor Vehicles)			



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

f / in / /floksertekstil

