

ZEUGMA FR

COMPOSITION / İÇERİK		BACKING / ZEMİN		
VINYL / URETHANE TOP COAT VİNİL / POLİÜRETAN YÜZEY		%100 POLYESTER		
TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		630 ± 5%	g/m ²	ISO 2286-2
TENSILE STRENGTH / KOPMA DİRENCİ	ACROSS / EN	> 200	N	ISO 1421
	ALONG / BOY	> 400	N	ISO 1421
TEAR STRENGTH / YIRTILMA DİRENCİ	ACROSS / EN	> 25	N	ISO 4674-1
	ALONG / BOY	> 25	N	ISO 4674-1
ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA	ACROSS / EN	255 ± 20	%	ISO 1421
	ALONG / BOY	75 ± 20	%	ISO 1421
ADHESION / YAPIŞMA		> 40	N	ISO 2411
MARTINDALE - ABRASION / AŞINMA DİRENCİ		> 75000	RUB(12kPa)	ISO 5470-2
MARTINDALE - ABRASION / AŞINMA DİRENCİ		> 100000	RUB	EN ISO 12947:1999 Part 2
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	≥ 5	GS	ISO 105X12
	WET / ISLAK	≥ 5	GS	ISO 105X12
LIGHT FASTNESS / IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	≥ 5	BW	ISO 105B02
	DARK COLORS / KOYU RENKLER	≥ 6	BW	ISO 105B02
ANTIMICROBIAL & ANTIFUNGAL ANTİMİKROBİYAL & ANTİFUNGİ	E. Coli (Growth under sample)		Good Effect	ISO 20645:2002
	K. Pneumoniae (Growth under sample)		Good Effect	
	S. Aureus (Growth under sample)		Good Effect	
FLAME RETARDANCY / GÜÇ TUTUŞURLUK	BS 7176 Low Hazard IMO FTP Code Annex 1 Part 8 FMVSS 302 (FR Standart of Motor Vehicles) BS 5852 Part 1 Ignition Source 0,1 (Cigarette & Match) EN 1021 part 1 and 2 ECE R 118 ANNEX 6,7,8			



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

f / in / /floksertekstil

