

MALCOLM

TECHNICAL CHARACTERISTICS / TEKNİK ÖZELLİKLER

FABRIC COMPOSITION / KUMAŞ İÇERİĞİ	%100 POLYESTER
---	-----------------------

TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		300 ± %10	g/m ²	ISO 2286-2
TEAR STRENGTH / YIRTILMA DİRENCİ	ACROSS / EN	> 20	N	ISO 13937-2
	ALONG / BOY	> 20	N	ISO 13937-2
TENSILE STRENGTH / KOPMA DİRENCİ	ACROSS / EN	> 300	N	ISO 1421
	ALONG / BOY	> 500	N	ISO 1421
ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA	ACROSS / EN	> 100	%	ISO 1421
	ALONG / BOY	> 50	%	ISO 1421
LAMINATION ADHESION / LAMİNASYON YAPIŞMASI		> 10	N	ISO 2411
MARTINDALE - ABRASION / AŞINMA DAYANIMI		> 5.000	RUB (12kPa)	ISO 12947
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	≥ 4,0	GS	ISO 105-X12
	WET / ISLAK	≥ 3,5	GS	ISO 105-X12



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

/floksertekstil

